

**HIGH BUILD EPOXY LININGS
CHEMICAL RESISTANCE CHART**

Fresh water	√
Salt water	√
Crude oil	√
Methanol	NR
15% Hydrochloric acid	√
20% Hydrochloric acid	√
20% HCL, 5% Xylene	√
20% HCL, 10% H ₃ PO ₄ , 10% H ₂ SO ₄	√
Fuel oil	√
Diesel	√
Gasohol	√
Gasoline	√

Key: √=resistant

NR=not recommended